

フロー値 (180±20mm)

	セメント (kg)	砂 (kg)	混練水 (kg)	希釀水 (kg)	起泡剤 アクアタフHD (kg)	空気量 (%)	湿潤密度 (g/cm³)	-軸圧縮強さ σ_{28} (KN/m²)
1 : 0	268	–	219	26.45	1.15	66.5	0.51	300
	298	–	235	25.53	1.11	64.0	0.56	500
	334	–	256	24.38	1.06	61.0	0.62	800
	353	–	264	23.69	1.03	59.5	0.64	1,000
	420	–	290	21.85	0.95	55.0	0.73	1,500
1 : 1	214	214	195	25.07	1.09	62.5	0.65	300
	300	300	201	22.31	0.97	56.0	0.82	1,000
1 : 2	250	500	202	20.01	0.87	50.0	0.97	1,000
	300	600	198	17.94	0.78	45.0	1.12	2,500
	340	600	237	15.87	0.69	40.0	1.19	2,500
1 : 3	200	600	179	20.01	0.87	50.0	1.00	1,000
	225	675	194	17.94	0.78	45.0	1.11	1,500
1 : 4	200	800	205	15.87	0.69	40.0	1.22	1,500
1 : 5	160	800	218	15.87	0.69	40.0	1.19	1,000